

POWERED BY **Dialog**

Conductive cellulose fibre prepn., for uniform conductivity - by treating fibre with reactive dye or isocyanate to react with hydroxyl gp. on cotton fibre, and coating surface with pyrrole polymer, preventing static charge
Patent Assignee: ACHILLES CORP

Patent Family

Patent Number	Kind	Date	Application Number	Kind	Date	Week	Type
JP 5059671	A	19930309	JP 91237099	A	19910823	199315	B

Priority Applications (Number Kind Date): JP 91237099 A (19910823)

Patent Details

Patent	Kind	Language	Page	Main IPC	Filing Notes
JP 5059671	A		4	D06M-015/356	

Abstract:

JP 5059671 A

The prepn. comprises treating (F') a cellulose fibre with (R1) a reactive dye or (R2) an isocyanate to react with the hydroxyl-gp. on (F') cellulose, and the surface of (F') is coated with (P) a pyrrole polymer or impregnated with a part or whole of (P) into (F').

Pref. prepn. comprises treating (F') cellulose fibre with (R1) or (R2) and contacting it with monomer of (P) to polymerise it in the presence of (C) an oxidising catalyst or opt. together with (D) a dopant to conjugate (P) with (F') giving conductivity.

(F) cellulose fibre is pref. cotton, hemp, rayon, etc..

(R1) reactive dye is pref. amino-anthraquinone, e.g. "Remazol" (RTM) obtd. from Hoechst KK; or benzidine, e.g. "Cibacron" (RTM) obtd. from Ciba Geigy KK.

(R2) isocyanate is pref. phenyl-, butyl-, toluene-di-isocyanate, etc.. The monomer of (P) is pref. 3-methyl-, N-methyl-pyrrole, etc..

USE/ADVANTAGE - The treated conductive cellulose is prevented from static charge giving no sparking; and used for making working clothes, etc. in IC producing work, or work handling inflammable materials

Dwg.0/0

Derwent World Patents Index

© 2004 Derwent Information Ltd. All rights reserved.

Dialog® File Number 351 Accession Number 9428378